

Research Report – UCD-ITS-RR-17-15

Fully Permeable Pavement for Stormwater Management: Progress and Obstacles to Implementation in California

November 2017

John T. Harvey Sifang Shan Hui Li David Jones Rongzong Wu

Fully Permeable Pavement for Stormwater Management: Progress and Obstacles to Implementation in California

Authors:

J. Harvey, S. Shan, H. Li, D. J. Jones, and R. Wu

Work Conducted Under Partnered Pavement Research Center Strategic Plan Element No. 2.8:
Advanced Pavement Research for Long-Term Future Needs

PREPARED FOR:

PREPARED BY:

California Department of Transportation Division of Research, Innovation, and System Information Office of Materials and Infrastructure University of California Pavement Research Center UC Davis, UC Berkeley





TECHNICAL REPORT DOCUMENTATION PAGE

1.	REPORT NUMBER UCPRC-TM-2017-03	7-03		RECIPIENT'S CATALOG NUMBER
4.	TITLE AND SUBTITLE Fully Permeable Pavement for Storr Implementation in California	5.	REPORT PUBLICATION DATE November 2017	
			6.	PERFORMING ORGANIZATION CODE
7.	AUTHOR(S) J. Harvey, S. Shan, H. Li, D. J. Jone	8.	PERFORMING ORGANIZATION REPORT NO. UCPRC-TM-2017-03	
9.	PERFORMING ORGANIZATION NA University of California Pavement Ro Department of Civil and Environmen	10.	WORK UNIT NUMBER	
	1 Shields Avenue Davis, CA 95616	11.	CONTRACT OR GRANT NUMBER 65A0542	
12.	SPONSORING AGENCY AND ADD California Department of Transporta Division of Research, Innovation, an P.O. Box 942873	tion	13.	TYPE OF REPORT AND PERIOD COVERED Technical Memorandum January 2016 to March 2017
	Sacramento, CA 94273-0001		14.	SPONSORING AGENCY CODE

15. SUPPLEMENTAL NOTES

16. ABSTRACT

Fully permeable pavements capture stormwater and infiltrate it into the ground and/or hold it until discharging it into stormwater conveyance. In either case, they offer benefits in terms of reducing or eliminating the need for stormwater conveyance infrastructure, capturing pollutants, and potentially reducing air temperatures around them. This technical memorandum reviews recent advances in structural design, materials, and hydraulic design that have filled many of the gaps in permeable pavement technology. The memo then presents the results of a recent survey in California, with some additional out-of-state responders, regarding awareness of permeable pavements and obstacles to their implementation. Finally, the memo presents recommendations for filling remaining knowledge gaps and overcoming obstacles to implementation.

 KEY WORDS permeable pavement, porous asphalt, pe permeable interlocking concrete, stormwa 			This document is available to the public onal Technical Information Service,
19. SECURITY CLASSIFICATION 20. NUMBER OF PAGE		GES	21. PRICE
(of this report)	21		None
Unclassified			
	D	and a first of the second second second second	1

Reproduction of completed page authorized

<u>UC</u>	PRC ADDIT	IONAL INFORM	/IATION					
1.	DRAFT STAGE Final			2. VERSION NUMBER 1				
3.		VEMENT RESEARCH IN ELEMENT NUMBER		4. DRISI TASK NUMBER 2685				
5.	CALTRANS TEC T. J. Holland	HNICAL LEAD AND RE	EVIEWER(S)	6. FHWA NUMBER CA182685A	R			
7.	PROPOSALS FOR IMPLEMENTATION None							
8.	Laboratory Testin T. Wang, R. Wu a No. UCPRC-RR-2	ng and Modeling for Stru and B. Campbell. Nover 2010-01). California De	mber 30, 2010. (Caltran	s Document No. CTSW	nents: Final Report. D. Jo V-RT-10-249.04; UCPRC Imental Analysis, Storm	Document		
9.	LABORATORY A The UCPRC labo	CCREDITATION ratory is accredited by <i>I</i>	AASHTO re:source for t	he tests listed in this re	eport	AASHID		
10.	SIGNATURES							
	T. Harvey RST AUTHOR	J.T. Harvey TECHNICAL REVIEW	D. Spinner EDITOR	J.T. Harvey PRINCIPAL INVESTIGATOR	T.J. Holland CALTRANS TECH. LEADS	T.J. Holland CALTRANS CONTRACT		

Reproduction of completed page authorized

UCPRC-TM-2017-03 iii

(This page left blank)

TABLE OF CONTENTS

	OF TABLES	
PROJ	ECT OBJECTIVES	vi
1 I	NTRODUCTION	1
1.1	Applications and Benefits of Permeable Pavements	
1.2		
2 R	ECENT ADVANCES	
2.1	Recent Advances in California	
2.2	Advances Outside of California	4
3 S	URVEY REGARDING OBSTACLES TO IMPLEMENTATION	5
3.1	Survey Description	5
3.2	Californians with Permeable Pavement Experience	6
3.3	Non-Californians with Permeable Pavement Experience	7
3.4	Californians without Permeable Pavement Experience	7
4 C	ONCLUSIONS AND RECOMMENDATIONS	10
REFE	RENCES	12
	LIST OF TABLES	
Table	3.1: Three Most Significant Issues Affecting Implementation of FPP	6
	3.2: Responses to Remaining Questions to Californians with FPP Experience.	
	3.3: Responses to Questions to Californians without FPP Experience	

DISCLAIMER

This document is disseminated in the interest of information exchange. The contents of this report reflect the views of the authors who are responsible for the facts and accuracy of the data presented herein. The contents do not necessarily reflect the official views or policies of the State of California or the Federal Highway Administration. This publication does not constitute a standard, specification or regulation. This report does not constitute an endorsement by the Department of any product described herein.

For individuals with sensory disabilities, this document is available in alternate formats. For information, call (916) 654-8899, TTY 711, or write to California Department of Transportation, Division of Research, Innovation and System Information, MS-83, P.O. Box 942873, Sacramento, CA 94273-0001.

PROJECT OBJECTIVES

The objective of this project was to begin to identify gaps in technology, information, benefits and/or incentives that are slowing or stopping the greater implementation of fully permeable pavement in the US, particularly in California. The objective was completed through a survey.

SI* (MODERN METRIC) CONVERSION FACTORS							
		XIMATE CONVERSION					
Symbol	When You Know	Multiply By	To Find	Symbol			
		LENGTH	New .				
in ft	inches feet	25.4 0.305	Millimeters Meters	mm			
		0.914	Meters	m m			
yd mi	yards miles	1.61	Kilometers	Km			
IIII	imics	AREA	Knoneces	Kili			
in ²	square inches	645.2	Square millimeters	mm^2			
ft ²	square feet	0.093	Square meters	m^2			
yd^2	square yard	0.836	Square meters	$\frac{m}{m^2}$			
ac	acres	0.405	Hectares	ha			
mi ²	square miles	2.59	Square kilometers	km ²			
		VOLUME	- 1				
fl oz	fluid ounces	29.57	Milliliters	mL			
gal	gallons	3.785	Liters	L			
ft ³	cubic feet	0.028	cubic meters	m^3			
yd ³	cubic yards	0.765	cubic meters	m ³			
<i>J</i> =	NOT	E: volumes greater than 1000 L sh					
		MASS					
oz	ounces	28.35	Grams	g			
lb	pounds	0.454	Kilograms	kg			
T	short tons (2000 lb)	0.907	megagrams (or "metric ton")	Mg (or "t")			
-	short tons (2000 ie)	TEMPERATURE (exact		1119 (01 1)			
°F	Fahrenheit	5 (F-32)/9	Celsius	°C			
1	ramemen	or (F-32)/1.8	Ceisius	C			
		ILLUMINATIO	N				
fo	foot-candles	10.76	Lux	lx			
fc fl	foot-Lamberts	3.426	candela/m ²	cd/m ²			
11				Cd/III			
11.0		ORCE and PRESSURE		N			
lbf lbf/in ²	poundforce	4.45	Newtons	N kPa			
101/111	poundforce per square inch	6.89	Kilopascals	KPa			
APPROXIMATE CONVERSIONS FROM SI UNITS							
	AFFROAL	MATE CONVERSION	IS FROM SI UNITS				
Symbol	When You Know	Multiply By	To Find	Symbol			
Symbol		Multiply By LENGTH		Symbol			
Symbol		Multiply By LENGTH 0.039	To Find Inches	in			
	When You Know millimeters meters	Multiply By LENGTH 0.039 3.28	To Find Inches Feet	in ft			
mm m m	When You Know millimeters meters meters	Multiply By LENGTH 0.039 3.28 1.09	To Find Inches Feet Yards	in ft yd			
mm m	When You Know millimeters meters	Multiply By LENGTH 0.039 3.28 1.09 0.621	To Find Inches Feet	in ft			
mm m m km	When You Know millimeters meters meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA	To Find Inches Feet Yards	in ft yd mi			
mm m m km	When You Know millimeters meters meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016	Inches Feet Yards Miles square inches	in ft yd mi in ²			
mm m km	when You Know millimeters meters meters kilometers square millimeters square meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764	Inches Feet Yards Miles square inches square feet	in ft yd mi in ² ft ²			
mm m m km	when You Know millimeters meters meters kilometers square millimeters square meters square meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195	Inches Feet Yards Miles square inches square feet square yards	in ft yd mi in ² ft ² yd ²			
mm m m km	when You Know millimeters meters meters kilometers square millimeters square meters square meters Hectares	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47	Inches Feet Yards Miles square inches square feet square yards Acres	in ft yd mi in ² ft ² yd ² ac			
mm m m km	when You Know millimeters meters meters kilometers square millimeters square meters square meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386	Inches Feet Yards Miles square inches square feet square yards	in ft yd mi in ² ft ² yd ²			
mm m m km mm² m² m² ha km²	when You Know millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME	Inches Feet Yards Miles square inches square feet square yards Acres square miles	in ft yd mi in² ft² yd² ac mi²			
mm m m km mm² m² m² ha km²	when You Know millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces	in ft yd mi in ² ft ² yd ² ac			
mm m km mm² m² m² ha km²	when You Know millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons	in ft yd mi in² ft² yd² ac mi² fl oz gal			
mm m km mm² m² m² ha km²	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³			
mm m km mm² m² m² ha km²	when You Know millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons	in ft yd mi in² ft² yd² ac mi² fl oz gal			
mm m km mm² m² m² ha km²	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³			
mm m m km mm² m² m² ha km² mL L m³ m³	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 355.314 1.307 MASS 0.035	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz			
mm m m km mm² m² m² m² ha km² mL L m³ m³ m³	millimeters meters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb			
mm m m km mm² m² m² ha km² mL L m³ m³	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb)	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton")	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees)	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			
mm m m km mm² m² m² m² ha km² mL L m³ m³ m³	millimeters meters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb)	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton")	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton") Celsius lux	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact 1.8C+32 ILLUMINATIO 0.0929	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton") Celsius	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact 1.8C+32 ILLUMINATIO	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit N	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton") Celsius lux candela/m²	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact 1.8C+32 ILLUMINATIO 0.0929	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit N foot-candles foot-Lamberts	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t")	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton") Celsius lux candela/m²	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact 1.8C+32 ILLUMINATIO 0.0929 0.2919	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit N foot-candles foot-Lamberts	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T °F fc fl			
mm m m km mm² m² m² ha km² mL L m³ m³ g kg Mg (or "t") °C	millimeters meters meters kilometers square millimeters square meters square meters Hectares square kilometers Milliliters liters cubic meters cubic meters grams kilograms megagrams (or "metric ton") Celsius lux candela/m²	Multiply By LENGTH 0.039 3.28 1.09 0.621 AREA 0.0016 10.764 1.195 2.47 0.386 VOLUME 0.034 0.264 35.314 1.307 MASS 0.035 2.202 1.103 TEMPERATURE (exact 1.8C+32 ILLUMINATIO 0.0929 0.2919 FORCE and PRESSURE (exact 1.8C+32)	Inches Feet Yards Miles square inches square feet square yards Acres square miles fluid ounces Gallons cubic feet cubic yards Ounces Pounds short tons (2000 lb) t degrees) Fahrenheit N foot-candles foot-Lamberts or STRESS	in ft yd mi in² ft² yd² ac mi² fl oz gal ft³ yd³ oz lb T			

^{*}SI is the symbol for the International System of Units. Appropriate rounding should be made to comply with Section 4 of ASTM E380 (Revised March 2003).

UCPRC-TM-2017-03 vii

1 INTRODUCTION

Fully permeable pavements are defined for the purposes of this study as those in which all layers are intended to be permeable and the pavement structure serves as a reservoir to store water during storm periods in order to minimize the adverse effects of stormwater runoff. The surface can be any permeable paving material, and most surfaces are typically are either pervious concrete, porous asphalt, or permeable interlocking pavers, or combinations of each of these. In this technical memorandum the term permeable pavement is used generically for fully permeable pavements with all surface types. The rest of the pavement structure consists of aggregate layers with numerous large interconnected air-voids that can store water and allow it to flow through them. The subgrade is often compacted less than for conventional pavements to help improve its permeability as well.

Permeable pavements can be designed to capture some or part of the rainfall and runoff from storms, and can include features for conveying water to conventional stormwater drainage systems when they reach their capacity for storage and/or infiltration.

1.1 Applications and Benefits of Permeable Pavements

Local governments around the world are interested in the development of fully permeable pavement designs as a potential stormwater management best management practice (BMP). Interest also continues to grow as climate change brings a greater risk of severe rainfall events in many regions, and as the spread of urbanization results in larger areas of impermeable hardscape.

The California Department of Transportation (Caltrans) has been interested in fully permeable pavement for use in state-owned, off-mainline pavement facilities such as maintenance yards and other parking areas, as well as for potential use in retrofitted shoulders that capture the runoff from mainline streets and highways. These applications are of particular interest where permeable pavement is cost-competitive or cost-advantageous compared to other BMPs, and in densely developed urban areas where the space available for BMPs, such as basins and bio-swales, is not available. Although permeable pavement may require specialized vacuum trucks to maintain permeability, some agencies have stated that this is less of a change of operations and easier to budget than the maintenance and purchase of filters and chemicals for mechanical devices or the intensive and specialized landscaping required for other BMPs. The California State Water Resources Control Board has a grant program that helps local government pay for installation of permeable pavement as part of low-impact development to reduce and prevent stormwater contamination of rivers, lakes, and streams. Other federal (including US Environmental Protection Agency [EPA]), regional, state, and local agencies have shown increased interest in permeable pavement for stormwater management. Permeable pavements have also been investigated as a means of helping to control localized heat islands for human thermal comfort (1).

1.2 Challenges 10 Years Ago

Since the late 1970s, a range of fully permeable pavement projects intended for light vehicles traveling at slow speeds have been constructed in a number of US states. Most of the information available in the literature features successful projects, although a few failed applications of the technology have been reported. However, further inspection has revealed that failures occurred in localized areas due to clogging of the permeable surface or to construction processes that resulted in severe surface raveling or cracking (2).

Most applications of permeable pavement in North America have been for pavements with no high-speed traffic or truck traffic (e.g., automobile parking lots), which is a reflection of road-owner concerns about durability.

Structural design methods for permeable pavements have mostly been empirical in nature, but success with this approach requires a supporting collection of comprehensive, long-term performance data for all of the expected design conditions—including different materials, climates, subgrades, and structural cross sections—along with a large factorial set of performance data that considers all of these design variable permutations. To date, little of this data is available, limiting the speed of technology development for fully permeable pavements because of the high cost of learning from inevitable failures.

A review of design practice across the United States (2) published in 2012 showed the very limited scope of applications at that time for fully permeable pavements, even by the leading firms specializing in that type of design. That limited scope of applications in 2011 was also reflected in the then recently produced National Asphalt Pavement Association (NAPA) (3), American Concrete Pavement Association (4), and Interlocking Concrete Pavement Institute (5) manuals for design of porous asphalt, pervious concrete pavements, and permeable interlocking concrete pavements, respectively.

In summary, these major challenges appeared to be stalling implementation of fully permeable pavements five to eight years ago:

- Lack of designs for applications other than light traffic
- Lack of information about hydraulic and structural performance (functional life), maintenance (frequency, best practices), and life cycle cost
- The use of land development standards that require full stormwater handling systems intended for impermeable pavement even when a permeable pavement is used, which essentially doubles costs

2 RECENT ADVANCES

2.1 Recent Advances in California

Beginning in 2008 and ending in 2013, the California Department of Transportation funded a multi-year series of projects at the University of California Pavement Research Center (UCPRC) that looked at the hydraulic performance of permeable pavements in the field and under accelerated pavement testing (6,7,8). As a part of that program, Caltrans also funded the development of mechanistic-empirical (ME) structural design methods for fully permeable pavements to handle heavy trucks with surfaces of porous asphalt, pervious concrete and concrete slabs cast with drainage holes (2). The structural design procedure developed used fatigue data for the respective surface materials from laboratory bending beam fatigue results and shear stress to strength data for porous granular base materials, and considered axle load spectra for loading as well as traffic speed for the asphalt designs. The procedure and resulting design tables also included consideration of an optional 150 mm (6 inch) pervious concrete subbase below the granular reservoir layer to provide greater confinement and therefore greater stiffness and shear strength. The results of this research were implemented in a design guidance document (9).

In addition, a life cycle cost analysis (LCCA) was performed to evaluate the net present value (NPV) economic costs of full-depth permeable pavement compared with conventional stormwater management alternatives (10) for stand-alone pavements and for shoulder retrofit of highways. The LCCA used materials and construction costs in California and conservative estimates of permeable pavement life and compared the life cycle costs with those estimated for other best management practices (BMPs) in another Caltrans study (11). The LCCA found that the fully permeable shoulder retrofit was cost-effective compared with the currently practiced BMPs in most scenarios.

The design procedure developed for Caltrans and based on laboratory testing and mechanistic analysis was not validated or calibrated with field data or accelerated pavement testing. Starting with the work done for asphaltand concrete-surfaced fully permeable pavements, the Concrete Masonry Association of California and Nevada in partnership with the Interlocking Concrete Pavement Institute (ICPI) engaged the UCPRC in 2013 to develop an ME design procedure for permeable interlocking concrete pavement (PICP), and to calibrate the method using accelerated pavement testing with the Heavy Vehicle Simulator (HVS). The results of this work (12,13) are being incorporated into a new ASCE design method for PICP (14).

2.2 Advances Outside of California

There have been a number of advancements outside of California as well, although only a few can be covered in this technical memorandum. A recent evaluation (2015) completed for the National Center for Sustainable Transportation identified recent advances and current knowledge as well as remaining gaps in knowledge and experience (15). The report found that large advances have been made across the country (this report includes references to a large number of studies) and addressed many of the gaps identified at the start of the Caltranssponsored UCPRC program in 2008. It also found that some gaps remained in the areas of materials, structural performance and their full-scale validation; hydraulic and water quality performance and their validation; information regarding maintenance and clogging resulting in loss of permeability; and life cycle cost analysis (LCCA) and environmental life cycle assessment (LCA) information.

Similar conclusions were drawn in a report prepared for the American Association of State Highway and Transportation Officials (AASHTO) on permeable shoulders (16) and the Federal Highway Administration (FHWA) reference document on sustainable pavements (17). The FHWA document states that preliminary research, although not yet validated by field sections or accelerated pavement testing, indicates that it may be possible to design and construct permeable pavements for the highway environment. All three of these documents (15,16,17) and the ASCE book *Permeable Pavements* (18) cover research needs, including the need for structural testing.

The Toronto and Region Conservation Authority completed a five-year paver and concrete permeable pavement parking lot evaluation that demonstrated that geotextiles do not impede flows to the subgrade, as well as comparisons of surface water runoff and groundwater quality which showed improvement compared to impermeable asphalt pavement (19). The study included an LCCA comparison to impermeable asphalt with an oil and grit separator and the permeable pavements showed cost savings when differences in water quality were included (20).

3 SURVEY REGARDING OBSTACLES TO IMPLEMENTATION

3.1 Survey Description

Considering the great advances made in the technology of fully permeable pavements over the past 10 years, a number of practitioners and researchers in the field have questioned the apparent slow pace of acceptance and use of permeable pavements. This has been the subject of panel discussions at recent pavement and stormwater management conferences.

To get a better idea of the reasons for this slow pace of market penetration, the California Department of Transportation recently commissioned a survey of practitioners and agencies in California regarding the implementation of fully permeable pavement. It was also extended to include some out-of-state responses. The survey aimed to understand the respondents' level of knowledge regarding fully permeable pavement (FPP), and the obstacles and gaps that must be addressed if there is to be more widespread implementation of this technology in California. The survey was composed of eight questions, with separate question sections targeting practitioners who have implemented FPP and those who have not. The primary subjects of the survey were city civil engineers and consultants in both road construction and storm drain departments.

The survey was developed in a way that directed respondents to specific questions based on whether or not they have experience implementing FPP. For those without FPP experience, the questions asked about their level of familiarity with FPP design layout, environmental benefits, cost effectiveness, and potential risks and challenges. For engineers with experience with FPP, the survey focused more on the results of the projects, the selection of state code and manuals, the method of hydraulic design, and what they believed are the reasons for resistance to widespread implementation of FPP.

Initially, representatives from all California cities with population over 25,000 were contacted (246 of the 478 cities in the state) via email or telephone. Representatives in 206 cities were reached and 39 responses were initially received. Additional outreach was made both within the state and to selected experienced persons outside the state. The breakdown of the final 64 respondents and their level of experience is summarized below:

• Californians with experience: 26

• Californians without experience: 31

• Non-Californians with experience: 7

The survey results are summarized in the following tables, separated by location (California and non-California cities) and by type of experience with FPP (with experience or without experience). In each table the question is

shown along with the number of respondents to that question, and the percentage of respondents for each answer. All non-Californian responses are with previous experience of FPP.

3.2 Californians with Permeable Pavement Experience

The first question put to those with experience asked them to identify their three most significant issues with FPP. The responses are shown in Table 3.1. The results show that maintenance, which likely means maintaining the permeability of the surface, was by far the most cited issue, appearing in nearly one fifth of the responses. Water ponding, which was cited by eight percent, is related. Higher cost, installation issues, quality of construction, conflicts with utilities, and lack of familiarity with the design methods were the next most prevalent issues.

Table 3.1: Three Most Significant Issues Affecting Implementation of FPP

Three Significant Issues	Maintenance	None so far	Higher cost
(37)*	18.9% [†]	13.5%	10.8%
Installation	Quality of construction	Conflict with utilities	Water ponding
10.8%	8.1%	8.1%	8.1%
Unfamiliarity with design	Not strong enough to withstand traffic	Non-compliance with current codes	Poor mix design
8.1%	2.7%	2.7%	2.7%
Public perception	Maintaining native soil stability		
2.7%	2.7%		

Number in parenthesis indicates number of respondents.

The remaining questions posed to the Californians with FPP experience are shown in Table 3.2. The results show that nearly two thirds of respondents thought that their FPP projects were successful, and about the same number thought that their stakeholders held that same opinion. Just over ten percent thought that the projects were not successful, and about the same percentage thought that their other stakeholders felt the same way. Nearly three quarters of practitioners would definitely consider using FPP again, and more than 90 percent would consider it.

The survey results indicate that the primary reason FPP was chosen was for its environmental benefits, followed by owner's preference. About 10 percent of the respondents selected FPP for its long-term cost savings. The results also show that a wide range of design manuals and methods were used, while hydraulic design generally did not follow any established standards.

[†] Number in boldface indicates percentage of respondents who considered this issue to be one of the top three in significance.

For those with FPP experience, it was generally thought that the top four reasons for the rare implementation were higher initial cost, maintenance costs and issues, general industry conservatism, and a lack of guidance and specifications.

3.3 Non-Californians with Permeable Pavement Experience

The answers from non-Californians with FPP experience were very similar to those from Californians, although they were somewhat more positive about their experiences. Conflict with existing regulations was an additional reason cited for lack of widespread implementation.

3.4 Californians without Permeable Pavement Experience

The answers to the questions posed to Californians without prior FPP experience are shown in Table 3.3. More than a third of those without experience were not convinced that FPPs work. About 35 percent were happy to evaluate FPP or were waiting for the right project to try it on (some overlap in the two possible answers). Those without experience cited maintenance concerns and the possibility that FPP might not work well as a pavement as the two most likely reasons for the lack of widespread implementation. There were also concerns about greater initial cost and that FPP might not work as a catchment. The predominant methods for stormwater runoff treatment used by these respondents are detention ponds, retention ponds, and no treatment (straight to receiving waters).

Only one third were aware of the reductions in pollutants generally attributed to FPP, and less than 15 percent were aware that FPP can reduce peak flows. About 10 percent were aware that FPP can help replenish groundwater.

Table 3.2: Responses to Remaining Questions to Californians with FPP Experience

	e project(s) a su	ccess? (26)*							
Yes	Both yes and no	No	Too soon to tell						
65.4% [†]	19.2%	11.5%	3.8%						
Did stakeholders	think the project	ct(s) a success?	(24)						
Yes	Too soon to tell	No	Mostly	Unaware of the problems during construction	Both yes and no				
62.5%	12.5%	8.3%	8.3%	4.2%	4.2%				
Would you consid	der FPP again?	(25)							
Yes	Depends on application	No	Maybe						
72.0%	20.0%	4.0%	4.0%						
Reasons for choo	osing FPP (33)								
Environmental benefits	Owner's preference	Long-term cost savings	Helping meet requirements	Lack of drainage system	Previous experience	To have an alternative	For pilot evaluation purpose	Aesthetics	Location
45.5%	18.2%	9.1%	9.1%	3.0%	3.0%	3.0%	3.0%	3.0%	3.0%
Reference manua	als used (26)								
None/Unknown	ICP Institute	CA C3 stormwater	Caltrans	SFPUC 2016 GI Typical	Roller Compacted Concrete	Field Engineers	APWA	Developed own specs	City codes
		guidebook		Details	Specs	Ziigiiieeis		own spees	
30.8%	23.1%	11.5%	7.7%	7.7%		3.8%	3.8%	3.8%	3.8%
30.8% Hydraulic design		11.5%	7.7%		Specs		3.8%	_	3.8%
	omethod used (A Outsourced to consulting firms	11.5%	7.7% Collaboration with university		Specs		3.8%	_	3.8%
Hydraulic design Literature + design manuals 35.3%	Outsourced to consulting firms 35.3%	11.5% 17) In-house design 29.4%	Collaboration with		Specs		3.8%	_	3.8%
Hydraulic design Literature + design manuals	Outsourced to consulting firms 35.3%	11.5% 17) In-house design 29.4%	Collaboration with university		Specs		3.8%	_	
Hydraulic design Literature + design manuals 35.3%	Outsourced to consulting firms 35.3%	11.5% 17) In-house design 29.4%	Collaboration with university		Specs		3.8% Difficulty in installation 2.2%	_	Lack of knowledge in managing FPP projects 2.2%

^{*} Number in parenthesis indicates number of respondents.

† Number in boldface indicates percentage of respondents who considered this issue to be one of the top three in significance.

Table 3.3: Responses to Questions to Californians without FPP Experience

01	Happy to								
applicability	evaluate it	Other	Waiting for the right projects	Unfamiliar topic	Would like to know more				
35.1% [†]	18.9%	18.9%	16.2%	5.4%	5.4%				
Speculated obstacle	es in impleme	ntation (78)							
Maintenance v	May not work as a pavement	Greater initial cost	May not work as a catchment	Lack of design guidelines	Conflicts w/ utilities	Industry resistance	Other	Contractors' lack of knowledge	
29.5%	26.9%	15.4%	10.3%	5.1%	3.8%	3.8%	3.8%	1.3%	
Level of familiarity	v (29) 1=lowes	t familiarity, 5	=highest familiar	rity					
2	3	1	4	5					
37.9%	31.0%	17.2%	10.3%	3.4%					
Current stormwater	r runoff treati	ment (46)							
Detention I pond	Retention pond	Straight to receiving water	Treatment plant	Other	Permeable pavement				
30.4%	30.4%	19.6%	8.7%	8.7%	2.2%				
Environmental ben	nefits of FPP	known to you (.	36)						
	eduction in eak volume	No knowledge	Replenishing groundwater	Infiltration & storage of stormwater	Less treatment space occupied	Reducing surface grade	Less noise when rains	Erosion control	Helping meeting ADA standard
36.1%	13.9%	11.1%	11.1%	11.1%	5.6%	2.8%	2.8%	2.8%	2.8%
Expectation of life	cycle cost of l	FPP compared	to conventional	pavements? (26))				
More	o not know enough bout overall cost	Lower	Not sure, but maintenance cost higher	Lower if a retention space is needed					L
53.8%	30.8%	7.7%	3.8%	3.8%					

^{*} Number in parenthesis indicates number of respondents.

† Number in boldface indicates percentage of respondents who considered this issue to be one of the top three in significance.

4 CONCLUSIONS AND RECOMMENDATIONS

The following are the conclusions from the search of existing literature:

- Significant progress has been made in the technical aspects of designing FPP.
- Improved information regarding good design will become available due to updates to various design methods and to ASCE standards.

Although it was not addressed in the survey reported in this technical memorandum, earlier UCPRC work for Caltrans identified the need to improve the mix designs for pervious concrete and porous asphalt to obtain both better durability and better long-term permeability. The conclusions that follow have been drawn solely from the survey reported here:

- Those who have used fully permeable pavement (FPP) and their stakeholders generally consider that the projects were successful.
- Although a significant percentage of practitioners remain unconvinced that FPP can work, many of those practitioners lack detailed knowledge of FPP and are unaware of its environmental benefits.
- Concerns about maintenance efficacy and the cost of FPP remain, as do issues with initial cost and construction quality and expertise.
- Potential users of FPP appear to lack sufficient information and/or knowledge about the information available covering subjects such as initial costs, maintenance frequency and methods, design guidelines, and the selection of projects for which FPP may be applied.
- Another major obstacle to increased use of FPP appears to be the inherent risk-averseness of would-be
 practitioners, due to a lack of rewards for innovation and a low tolerance for failure that is common in
 many areas of civil engineering.

Following are recommendations for the research and development community working to improve and more fully implement permeable pavement technology:

- Develop more definitive information regarding the following items and make it more widely available.
 These should include basic information, how to determine the information for specific projects, and case study examples:
 - o Cost comparisons with alternatives (initial costs and life cycle costs)
 - Better documentation of benefits, disbenefits, and costs relative to alternatives in different design contexts
 - o Functional lives, for both structural and hydraulic (permeability) requirements
 - o New design information for all FPP types as it is produced
 - Develop and make known additional alternative best practices for maintenance and tradeoffs regarding their costs, difficulty, availability, and how frequently to perform them

- More field and accelerated pavement testing validation of designs
- Improvement of porous asphalt and pervious concrete mix designs

REFERENCES

- 1. Li, H., J. Harvey, T. J. Holland, and M. Kayhanian. 2013. The Use of Reflective and Permeable Pavements as a Potential Practice for Heat Island Mitigation and Stormwater Management. Environmental Research Letters 8 (1), 015023.
- Li, H., D. Jones, and J. Harvey. 2012. Development of Mechanistic-Empirical Design Procedure for Fully Permeable Pavement under Heavy Traffic. Transportation Research Record: Journal of the Transportation Research Board 2305, pp 83-94.
- 3. Hansen, K. 2008. Porous Asphalt Pavements for Stormwater Management. Lanham, MD: National Asphalt Pavement Association. (Information Series 131).
- 4. American Concrete Pavement Association. 2009. Stormwater Management with Pervious Concrete Pavement. Skokie, IL.
- 5. Smith, D.R. 2006. Permeable Interlocking Concrete Pavements. Selection, Design, Construction, and Maintenance. Herndon, VA. Interlocking Concrete Pavement Institute.
- 6. Kayhanian, M., D. Anderson, J.T. Harvey, D. Jones, and B. Muhunthan. 2012. Permeability Measurement and Scan Imaging to Assess Clogging of Pervious Concrete Pavements in Parking Lots. Journal of Environmental Management 95(1): 114-123.
- 7. Chai, L., M. Kayhanian, B. Givens, J.T. Harvey, D. Jones. 2012. Hydraulic Performance of Fully Permeable Highway Shoulder for Storm Water Runoff Management. ASCE Journal of Environmental Engineering, Volume 138(7), 711-722.
- 8. Coleri, E., M. Kayhanian, J. Harvey, K. Yang, and J. Boone. 2013. Clogging Evaluation of Open Graded Friction Course Pavements Tested under Rainfall and Heavy Vehicle Simulators. Journal of Environmental Management 129:164-172.
- 9. California Department of Transportation. 2014. Pervious Pavement Design Guidance, Division of Design, Office of Storm Water Management, August. www.dot.ca.gov/hq/oppd/stormwtr/bmp/DG-Pervious-Pvm_082114.pdf (Accessed April 14, 2017)
- 10. Wang, T., J. Harvey, and D. Jones. 2010. A Framework for Life-Cycle Cost Analyses and Environmental Life Cycle Assessments for Fully Permeable Pavements. Report CTSW-TM-10-249.03. www.ucprc.ucdavis.edu/PDF/UCPRC-TM-2010-05.pdf (Accessed December 9, 2016)
- 11. Caltrans. 2003. Caltrans Retrofit Program Final Report. Caltrans Division of Environmental Analysis. Report No. CTSW-RT-01-050. Sacramento, CA.
- 12. Jones, D., H. Li, R. Wu, J. Harvey, and D. Smith. 2016. Full-Scale Structural Testing of Permeable Interlocking Concrete Pavement to Develop Design Guidelines. ASCE World Environmental and Water Resources Congress 2016: pp. 351-363.

- 13. Li, H., D. Jones, R. Wu, J. Harvey, and D. Smith. 2016. Permanent Deformation Characterization of Permeable Interlocking Concrete Pavement Materials through Accelerated Pavement Testing. Construction and Building Materials (accepted).
- 14. Hein, D., and D. Smith. 2016. How Should You Be Designing Your Permeable Pavements? New ASCE Standard. StormCon2016. www.forester.net/stormcon-papers/sc16-papers/Hein_G41.pdf (Accessed December 9, 2016)
- 15. Kayhanian, M., P. Weiss, J. Gulliver, L. Khazanovich. 2015. The Application of Permeable Pavement with Emphasis on Successful Design, Water Quality Benefits, and Identification of Knowledge and Data Gaps. Summary Report, National Center for Sustainable Transportation. ncst.ucdavis.edu/wp-content/uploads/2014/08/09-30-2015-NCST-SR-Permeable-Pavement-FINALv5.pdf (Accessed December 9, 2016)
- 16. Hein, D. 2013. Permeable Shoulders with Stone Reservoirs. *onlinepubs.trb.org/onlinepubs/nchrp/docs/NCHRP25-25(82)_FR.pdf* (Accessed April 14, 2017)
- 17. Van Dam, T.J., J. T. Harvey, S. T. Muench, K. D. Smith, M.B. Snyder, I. L. Al-Qadi, H. Ozer, J. Meijer, P. V. Ram, J. R. Roesler, and A. Kendall. 2015. Towards More Sustainable Pavements: A Reference Document. Federal Highway Administration. HIF-15-002. www.fhwa.dot.gov/pavement/sustainability/hif15002/hif15002.pdf (Accessed April 14, 2017)
- 18. ASCE Permeable Pavements Task Committee. 2015. Permeable Pavements.
- 19. Toronto and Region Conservation, University of Toronto, 2015. Five Year Performance Evaluation of Permeable Pavements—Kortright, Vaughan: Final Report. www.sustainabletechnologies.ca/wp/wp-content/uploads/2016/02/KPP-Ext_FinalReport_Dec2015.pdf (Accessed April 14, 2017)
- 20. Sustainable Technologies Evaluation Program. 2015. Performance Evaluation of Permeable Pavements Technical Brief. www.sustainabletechnologies.ca/wp/wp-content/uploads/2015/01/PP-Tech-Brief-Final.pdf (Accessed April 14, 2017)